



MOLYKOTE® Longterm 2/78 US Grease

High-performance mineral-oil-based grease for metal-to-metal combinations with slow to moderately rapid movements

Features

- High load-carrying capacity
- Resistance to oxidation
- Good water washout performance
- Compatible with many elastomers
- No intentional polytetrafluoroethylene (PTFE) or per- and polyfluoroalkyl substances (PFAS)

Composition

- Mineral-oil-based grease
- Lithium soap thickener
- Solid lubricants, corrosion inhibitors and oxidation inhibitors

Applications

Suitable for metal-to-metal friction contacts with high stresses and low to moderate speeds. Designed for use in automobile and mobile equipment applications, including tie-rod linkages, axle rod linkages and ball joints.

How to use

Clean the contact areas. Apply MOLYKOTE® Longterm 2/78 US Grease by brush, grease gun, or automatic lubricating systems. The product can be used in centralized lubrication systems.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored at or below 20°C in its original and unopened containers, this product has a usable life of 60 months from the date of production.

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
	Color		Black
Base grease properties			
ASTM D217	Worked penetration (60 strokes)	mm/10	265-295
ASTM D70	Density	g/ml	0.93
ASTM D445	Base oil viscosity (@ 40°C)	mm ² /s	106
ASTM D1742	Oil separation (80°C/24 h)	wt-%	<6
CTM 0033A	Bleed (100°C/24 h)	wt-%	2
CTM 0033A	Evaporation (100°C/24 h)	wt-%	0.4
Temperature			
	Service temperature	°C	-35 to +130
ASTM D2265	Drop point	°C	>178
ASTM D1478	Low-temperature torque		
	Starting (-20°C)	Nm	220x10 ⁻³
	Running (-20°C)	Nm	20x10 ⁻³
	Starting (-30°C)	Nm	740x10 ⁻³
	Running (-30°C)	Nm	60x10 ⁻³
Load capacity			
ASTM 2566	Four ball wear (60 kg)	mm	0.6
ASTM 2596	Four ball weld	kg	>260

⁽¹⁾ASTM: American Society for Testing and Materials. CTM: Corporate Test Method; copies of CTMs are available on request. DIN: Deutsche Industrie Norm.

Continued on next page

Typical properties (continued)

Standard ⁽¹⁾	Test	Unit	Result
Oxidation, corrosion and water performance			
ASTM D942	Oxidation resistance (99°C/100 hr)	bar	0.1
ASTM D1264	Water washout (79°C/1 hr)	%	2
ASTM D6138	SKF – Emcor (DI water)		0-1

⁽¹⁾ASTM: American Society for Testing and Materials. CTM: Corporate Test Method; copies of CTMs are available on request. DIN: Deutsche Industrie Norm.

Packaging

This product is available in different standard container sizes as shown on molykote.com. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 2010-2024 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.